



TP-SS2 Stainless Steel Tape

Product Application & Description

TP-SS2 is a 2.0 mil. annealed stainless steel foil tape which incorporates a high-performance acrylic adhesive designed for permanent adhesion in a wide range of applications. TP-SS2 provides an aggressive adhesion performance, high shear and an outstanding high temperature resistance at service temperatures in excess of 400°F. The 76# poly coated liner offers excellent lay flat and smooth release.

Shelf Life & Storage

It is recommended to consume all materials within 1 year from date of purchase. Best if stored in a controlled environment (72°F and 50% RH) and out of direct sunlight.

0.002" 302/304 Series Annealed Stainless Steel Foil

This Metal Can Be Certified to ASTM-A-240, A-666 or Other Various Specifications

Technical Data

| Test Method/Performance Parameter | Result/Performance Properties |
|-------------------------------------|---------------------------------|
| Tape Thickness Without Liner | 5.0 mils. Nominal |
| 180° Peel @ 30 Min. (PSTC-101) | 3.75 lbs/in. |
| 180° Peel @ 20 Min. (ABS Substrate) | 2.3 lbs./in. |
| Shear (1" x 1" x 500 g.) | +150.0 Hours |
| Service Temperature | -20°F to 400°F (-29°C to 205°C) |
| Application Temperature | 45°F to 120°F (5°C to 49°C) |

Tested at 3.0 mil. of adhesive on 2.0 mil. polyester film to stainless steel.

Please Note: The information contained herein is derived from data believed to be reliable and is presented to assist our customers in determining whether our products are suitable for use in their application. We request that our customers test our products before use to satisfy themselves as to suitability for use. No warranty or guarantee is expressed or implied. Protection from any law or patents is not inferred. All patent rights are reserved. The exclusive remedy for all proven claims is limited to replacement of our materials and in no event shall we be liable for special, incidental or consequential damages. Customers desiring assistance with specification, development or performance criteria for specific product applications should contact us for further information.

16100 Imperial Parkway, Strongsville, OH 44149
1.800.521.0054 • info@allfoils.com